

1. Field of the Invention

In a known resolver stator, a stator coil wound around magnetic poles of the resolver stator is generally impregnated with a varnish using an epoxy, the varnish being dried and cured, for fixing the stator coil to the resolver stator.

A melted resin covers the overall stator coil including terminals and is cured.

The known resolver stator having the above configuration has problems described below.

When the resolver stator is used in an environment in which temperature varies in a wide range, cracks which cause

In manufacturing a known stator coil, the varnish must be cured at a high temperature; therefore, a temperature-controlled bath is necessary and manufacturing costs are increased because of the temperature control.

SUMMARY OF THE INVENTION

To the end, according to an aspect of the present invention, a resolver stator comprises a stator coil

including a plurality of winding portions each wound around a magnetic pole via ring-shaped insulation caps, the stator coil being impregnated with a liquid or melted resin and fixed to the magnetic poles by curing the resin. The resin is softer than an epoxy. The resin may be silicone. A peripheral part of one of the ring-shaped insulation caps may be provided with a plurality of terminals. Wire ends of the stator coil may be each wound around one of the plurality of terminals such that each wire end and the terminal form a winding-connecting part. The wire end and the terminal may be fixed to each other by soldering or fusing at one portion of the winding-connecting part and be independent from each other at the remaining portion of the winding-connecting part such that the wire end disposed in the remaining portion of the winding-connecting part is formed as a free wire end. The free wire end may be wound around the terminal at least once. The free wire end may be wound around the terminal a plurality of times. The free wire end may have a resilient function and slack.

The resolver stator according to the present invention offers advantages described below.

The stator coil is fixed to the magnetic poles of the resolver stator via a resin, such as silicone, which is softer than that of an epoxy which is used for a known resolver stator. The resin such as silicone has elasticity

10002499-43334

A part of the wire end of the stator coil wound around the terminal provided at the ring-shaped insulation cap is not fixed to the terminal and has a slack so as to have a resilient function. Therefore, deformation due to thermal expansion, vibration, and the like can be absorbed, whereby disconnection can be avoided, and a reliable resolver stator is obtainable.

Fig. 2 is a sectional view of the resolver stator shown in Fig. 1;

A resolver stator 2 shown in Fig. 1 includes a stator coil 1 of which winding portions are each wound via ring-shaped insulation caps 21 and 22 around a magnetic pole 20 which is a steel core. In Fig. 1, a rotor 1A is disposed inside the resolver stator 2. The winding portions of the stator coil 1 wound around the magnetic poles 20 are connected in series to each other via crossover wires 23.

A peripheral part 25, which is a part of the ring-shaped insulation cap 21 protruding in a radial direction, is positioned in a part of a rim 24 of the resolver stator 2. The peripheral part 25 is provided with terminals 4 standing at the peripheral part 25.

The terminals 4 are each formed integrally with a base 26 such that the each terminal 4 and the base 26 are connected to each other in an L-shape, as shown in Fig. 4. Each base 26 is connected to a lead wire 27. The terminals 4 protrude to the outside, each passing through a hole (not shown) formed in the peripheral part 25.

A liquid or melted resin 10 is applied to the surfaces of the magnetic poles 20 and the peripheral part 25 by potting or the like. The stator coil 1 provided on the magnetic poles 20 is impregnated with the resin 10 and is fixed to the magnetic poles 20 at the winding portions of the stator coil 1. The terminals 4 are affixed at the peripheral part 25.

In Figs. 1 and 2, the resin 10 is applied to dotted parts of the resolver stator 2. The resin 10 is, for example, silicone which is softer than an epoxy which forms a known varnish. It is not necessary to cure the resin 10 at a high temperature after being applied to the resolver stator 2, as in a case of the known varnish, and the resin 10 moves into a slightly elastic solid state by natural

4082459.42504

Since the resin 10 is sufficiently elastic so as not to be cracked when the resolver stator 2 is used in an environment in which temperature varies in a wide range.

Each wire end 3 (see Fig. 6) of the stator coil 1 wound around the magnetic poles 20 is wound around the terminal 4 a plurality of times, as shown in Fig. 7. The terminal 4 and the wire end 3 form a winding-connecting part 5.

In Fig. 8, when the stator coil 1 extends in a direction A due to heat or vibration received from the outside in the direction A or in a direction B perpendicular to the direction A, the extension and the vibration can be substantially absorbed by a resilient function and a slack

The free end 30 may have the function of a spring when the wire end 3 is wound one time or less than one time, for example, by 300 degrees or 250 degrees, instead of being wound a plurality of times.